

Received: 08/31/2010		Completed: 09/01/2010		Letter: Z1	her	P.O.#: 10200	Test Report #:	2-84415-1-
Client's Identification		Teepee/Rodeo (Brown Mat Hide)						
Tested For:		Key Test: UFAC Fabric					115	
		Ecopell/GmbH 87480 Weitnau Germany,					Tel: 1-( )- - Fax: 1-( )- - Ext:	

PC.4H

TEST PERFORMED: UFAC Fabric Classification Test Method 1990  
Cigarette Ignition Resistance of Fabric Intended for Use in Upholstered Furniture

RESULTS:	TEST		RETEST (If Required)	
	Ignition (yes/no/SE)	Char Length on Vertical Panel (inches)	Ignition (yes/no/SE)	Char Length on Vertical Panel (inches)
Specimen #				
1	SE	0.0	SE	0.0
2	SE	0.0	SE	0.0
3	SE	0.0	SE	0.0

#### ABBREVIATION WHICH MAY BE USED:

SE: Indicates that the cigarette self-extinguished prior to burning its entire length. When this occurs, a "retest" of that specimen is performed.

#### CLASSIFICATION SYSTEM:

Class I - For each specimen: No obvious ignition; char length less than 1.75".  
(Indicates propensity to resist cigarette ignition in conjunction with standard foam filling material.)

Class II - For any specimen: Obvious ignition or char length 1.75" or greater.  
(Indicates inability to resist cigarette ignition in conjunction with standard foam filling material.)

#### RETEST PROVISION:

Applies only to cigarettes that self-extinguish. It does not apply to specimens which ignite or have a char length of 1.75" or greater.

CONCLUSION: Based on the above Results and Criteria, the item tested is assigned a:

☒ Class I rating; ☐ Class II rating

Received: 08/31/2010	Completed: 09/01/2010	Letter: Z1	her	P.O.#: 10200	Test Report #:	2-84415-1-
Client's Identification						
Tested For: Ecopell/GmbH 87480 Weimau Germany,						
Key Test: UFAC Fabric						
Tel: 1- ( ) - Fax: 1- ( ) - Ext: 115						

REMARKS : None.

COMMENTARY: The cigarette ignition source used in this test conforms to the physical parameters set forth in the test standard. The actual propensity of the cigarette (that is currently manufactured) to cause ignition of materials under test might be less than the cigarette that was manufactured at the inception of the test standard.


CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by UFAC Fabric Classification Test Method 1990.

*Heather E. Robertson*

AUTHORIZED SIGNATURE  
 THE GOVMARK ORGANIZATION, INC. / ec

MS. HEATHER ROBERTSON  
 SEP 2 8 2010

(Page 2 of 2)



Received: 08/31/2010		Completed: 09/01/2010		Letter: Y1	her	P.O.#: 10200	Test Report #:	2-84414-1-
Client's Identification		Teepee/Glamour (Brown Glossy Hide)						
Tested For: Ecopell/GmbH 87480 Weimau Germany, Key Test: UFAC Fabric 115								
Tel: 1- ( ) - Fax: 1- ( ) - Ext:								

TEST PERFORMED: UFAC Fabric Classification Test Method 1990  
 Cigarette Ignition Resistance of Fabric Intended for Use in Upholstered Furniture

RESULTS:	TEST	Char Length on Vertical Panel	Ignition (yes/no/SE)	Char Length on Vertical Panel	Ignition (yes/no/SE)	Char Length on Vertical Panel	RETEST (If Required)
1	SE	0.0	SE	0.0	SE	0.0	-----
2	SE	0.0	SE	0.0	SE	0.0	-----
3	SE	0.0	SE	0.0	SE	0.0	-----

ABBREVIATION WHICH MAY BE USED:

SE: Indicates that the cigarette self-extinguished prior to burning its entire length. When this occurs, a "retest" of that specimen is performed.

CLASSIFICATION SYSTEM:

Class I - For each specimen: No obvious ignition; char length less than 1.75". (Indicates propensity to resist cigarette ignition in conjunction with standard foam filling material.)

Class II - For any specimen: Obvious ignition or char length 1.75" or greater. (Indicates inability to resist cigarette ignition in conjunction with standard foam filling material.)

RETEST PROVISION:

Applies only to cigarettes that self-extinguish. It does not apply to specimens which ignite or have a char length of 1.75" or greater.

CONCLUSION: Based on the above Results and Criteria, the item tested is assigned a: [x] Class I rating; [ ] Class II rating

Received:08/31/2010		Completed:09/01/2010		Letter: Y1	her	P.O.#: 10200	Test Report #:	2-84414-1-
Client's Identification		Teepee/Glamour (Brown Glossy Hide)						
Tested For:		Ecopell/GmbH 87480 Weitnau Germany,						
		Tel: 1- ( ) - Fax: 1- ( ) - Ext:						
		Key Test: UFAC Fabric						
		115						

REMARKS : None.

COMMENTARY: The cigarette ignition source used in this test conforms to the physical parameters set forth in the test standard. The actual propensity of the cigarette (that is currently manufactured) to cause ignition of materials under test might be less than the cigarette that was manufactured at the inception of the test standard.

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by UFAC Fabric Classification Test Method 1990.

*Heather E. Robertson*

AUTHORIZED SIGNATURE  
THE GOVMARK ORGANIZATION, INC. / ec

MS. HEATHER ROBERTSON

SEP 2 8 2010

(Page 2 of 2)

Received: 08/31/2010		Completed: 09/01/2010		Letter: Y	her	P.O.#: 10200	Test Report #:	2-84414-0-
Client's Identification		Teepee/Glamour (Brown Glossy Hide)						
Tested For:								
Ecopell/GmbH 87480 Weimau Germany,								
Tel: 1- (-) - Fax: 1- (-) - Ext:								
105								

CA 117: LE 2000; R 7/09; V 7/09      PC: .5H+.5H      DL/Jd

TEST PERFORMED: California Technical Bulletin 117 (March 2000) Section E Upholstery Fabrics

RESULTS:		LENGTH		Burning Time		Specimen		Burning Time		WIDTH	
Avg:		Avg:		Avg:		Avg:		Avg:		Avg:	
#1	Face	DNI	Face	#6	Face	DNI	Face	#6	Face	DNI	Face
#2	Face	DNI	Face	#7	Face	DNI	Face	#7	Face	DNI	Face
#3	Face	DNI	Face	#8	Back	DNI	Back	#8	Back	DNI	Back
#4	Back	DNI	Back	#9	Back	DNI	Back	#9	Back	DNI	Back
#5	Back	DNI	Back	#10	Back	DNI	Back	#10	Back	DNI	Back

NOTE: This is a minimal flammability test to screen out highly flammable materials.

REMARKS: None.

ACCEPTANCE CRITERIA: Shall meet Class I of CS 191-53 --

[x] Plain Surface Materials: 3.5 Seconds or No Recordable Burning Time  
[ ] Raised Surface Materials: 7.0 Seconds or No Recordable Burning Time

ABBREVIATIONS OF "NO RECORDABLE BURNING TIME" CATEGORIES:

DNI = Did not ignite when exposed to test ignition source.  
IBE = Ignited but extinguished before burning through stopcord.  
SF = Surface flash only; stopcord not burned & no burning/charring/fusing of the base fabric.  
TSF = Timed surface flash; stopcord burned, but no burning/charring/fusing of the base fabric.

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:

[x] Complies; [ ] Does not comply

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by California Technical Bulletin 117 (March 2000) Section E Upholstery Fabrics.

*Heather S. Robertson*  
AUTHORIZED SIGNATURE  
THE GOVMARK ORGANIZATION, INC. / ec  
MS. HEATHER ROBERTSON

Received: 08/31/2010		Completed: 09/01/2010		Letter: X1	her	P.O.#: 10200	Test Report #:	2-84413-1-
Client's Identification		Ecopell/Napa (green hide)						
Tested For: Ecopell/GmbH 87480 Weimau Germany,								
Tel: 1- ( ) - Fax: 1- ( ) - Ext: 115								
Key Test: UFAC Fabric								

TEST PERFORMED: UFAC Fabric Classification Test Method 1990  
Cigarette Ignition Resistance of Fabric Intended for Use in Upholstered Furniture  
PC, 4H

RESULTS:		TEST		RETEST (If Required)	
Specimen #		Ignition (yes/no/SE)		Ignition (yes/no/SE)	
Char Length on Vertical Panel		Char Length on Vertical Panel		Char Length on Vertical Panel	
1	SE	0.0	SE	0.0	SE
2	SE	0.0	SE	0.0	SE
3	SE	0.0	SE	0.0	SE

SE: Indicates that the cigarette self-extinguished prior to burning its entire length. When this occurs, a "retest" of that specimen is performed.

CLASSIFICATION SYSTEM:

Class I - For each specimen: No obvious ignition; char length less than 1.75".  
(Indicates propensity to resist cigarette ignition in conjunction with standard foam filling material.)

Class II - For any specimen: Obvious ignition or char length 1.75" or greater.  
(Indicates inability to resist cigarette ignition in conjunction with standard foam filling material.)

RETEST PROVISION:

Applies only to cigarettes that self-extinguish. It does not apply to specimens which ignite or have a char length of 1.75" or greater.

CONCLUSION: Based on the above Results and Criteria, the item tested is assigned a:  
[x] Class I rating; [ ] Class II rating

Received: 08/31/2010		Completed: 09/01/2010		Letter: X1	her	P.O.#: 10200	Test Report #:	2-84413-1-
Client's Identification		Ecopell/Napa (green hide)						
Tested For:								
Ecopell/GmbH 87480 Weimau Germany,								
Tel: 1- ( ) - Fax: 1- ( ) - Ext:								
Key Test: UFAC Fabric 115								

REMARKS : None.

COMMENTARY: The cigarette ignition source used in this test conforms to the physical parameters set forth in the test standard. The actual propensity of the cigarette (that is currently manufactured) to cause ignition of materials under test might be less than the cigarette that was manufactured at the inception of the test standard.

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by UFAC Fabric Classification Test Method 1990.

*Heather S. Robertson*  
 \_\_\_\_\_  
 AUTHORIZED SIGNATURE

THE GOVMARK ORGANIZATION, INC. / ec  
 MS. HEATHER ROBERTSON  
 SEP 2 8 2010

(Page 2 of 2)

Received: 08/31/2010	Completed: 09/01/2010	Letter: X	her	P.O.#: 10200	Test Report #:	2-84413-0-
Client's Identification		Ecopell/Napa (green hide)				
Tested For:						
Ecopell/GmbH 87480 Weitnau Germany,						
Tel: 1- ( ) - Fax: 1- ( ) - Ext:						
Key Test: CA 117 E						
105						

CA 117: LE 2000; R 7/09; V 7/09 PC: .5H+.5H DL/Jd

TEST PERFORMED: California Technical Bulletin 117 (March 2000) Section E Upholstery Fabrics

RESULTS:	LENGTH	Burning Time	Specimen	Face	Back	Avg:
#1	DNI			Face	Back	
#2	DNI			Face	Back	
#3	DNI			Face	Back	
#4	DNI			Back	Back	
#5	DNI			Back	Back	
Avg:						

RESULTS:	WIDTH	Burning Time	Specimen	Face	Back	Avg:
#1	DNI			Face	Back	
#2	DNI			Face	Back	
#3	DNI			Face	Back	
#4	DNI			Back	Back	
#5	DNI			Back	Back	
Avg:						

NOTE: This is a minimal flammability test to screen out highly flammable materials.

REMARKS: None.

ACCEPTANCE CRITERIA: Shall meet Class I of CS 191-53 --

Minimum Average Burning Time (Flame Spread)

[x] Plain Surface Materials:	3.5 Seconds or No Recordable Burning Time
[ ] Raised Surface Materials:	7.0 Seconds or No Recordable Burning Time

ABBREVIATIONS OF "NO RECORDABLE BURNING TIME" CATEGORIES:

DNI = Did not ignite when exposed to test ignition source.  
IBE = Ignited but extinguished before burning through stopcord.  
SF = Surface flash only; stopcord not burned & no burning/charring/fusing of the base fabric.  
TSF = Timed surface flash; stopcord burned, but no burning/charring/fusing of the base fabric.

CONCLUSION: Based on the above Results and Acceptance Criteria, the item tested:

[x] Complies; [ ] Does not comply

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by California Technical Bulletin 117 (March 2000) Section E Upholstery Fabrics.

AUTHORIZED SIGNATURE

HEATHER ROBERTSON

THE GOVMARK ORGANIZATION, INC. / ec