



DATA SHEET



TESTED FOR	RESULT	CONFIRM TO DIN
Lightfastness:	1	54004
Possible color change:		
Abrasion values:	Level:	
Dry	5	53339
Wet	5	
Perspiration	5	
Permanent folding behavior: 20.000 bucklings	passed	53340
Tensile strength: 20 N/mm	passed	53329
Burning behavior: y EN1021 part I u. II	passed	
<p>Detaillied information about light fastness, abrasion values, skin tollernace and burning behaviour can be found at: www.vegetable-tanned-leather.com/data-and-facts.html</p>		
<p>Tested for Heavy metals, aniline and p-Phenylendiamin, Chlorinated paraffins (Conducted by the German Institute of Environment in Bremen, 2013/2017)</p>		

BABY BLUE 300



Color: Baby Blue 300
 Collection: Nappa
 Thickness: 1,4 - 1,6 mm



* Valid only for skins from eco farming
 (Please ask for availability)

DATA SHEET



Results of the examination for heavy metals

Heavy metals	H 8252 FL-5 Ecopell 300 Baby Blau KW 46 (mg/kg)	BG (mg/kg)	Requirements IVN Leather (mg/kg)
Antimony	<0,5	0,1	1
Aluminium	50	10	500
Arsenic	<0,5	1	1
Lead	<0,5	0,1	1
Cadmium	<0,2	0,2	0,2
Chrome	18	2	50
Cobalt	<1	1	5
Mercury	<0,1	0,1	0,2
Nickel	<1	1	5
Titanium	<10	10	500
Zirconium	<5	5	500

Results of the examination for chlorinated paraffins

Parameter	H 8696 FL-8 Ecopell 300 Baby Blue KW 7 (mg/kg)	NG (mg/kg)	Requirements IVN Leather (mg/kg)
Chlorinated paraffins (C10 - C13)	nn	50	100

Results of the examination for aniline and p-Phenylendiamin

Parameter	K 4659 FL - 4 Ecopell 300 Baby Blau [mg/kg]	NG (mg/kg)
Aniline	nn	3
p-Phenylendiamin	nn	5

* Sum limit for further amines going beyond European legislation
(2,4 Xylidine, N,N. Dimethylaniline, 5-Chlorine-o-toluidine, p-Phenylenediamine and Aniline)

BG = limit of determination | NG = detection limit | mg/KG = milligram per kilogram | nn = not detected