

# DATA SHEET



TESTED FOR	RESULT	CONFIRM TO DIN
------------	--------	----------------

CRANBERRY 321
---------------

Lightfastness:	5-	54004
----------------	----	-------

Abrasion values:	Level:	
Dry	2 - 3	53339
Wet	1 - 2	
Perspiration	1 - 2	

Permanent folding behavior: 20.000 bucklings	passed	53340
---	--------	-------

Tensile strength: 20 N/mm	passed	53329
------------------------------	--------	-------

Burning behavior: EN1021 part I u. II	passed	
--	--------	--

Detaillied information about light fastness, abrasion values, skin tollernace and burning behaviour can be found at:  
[www.vegetable-tanned-leather.com/data-and-facts.html](http://www.vegetable-tanned-leather.com/data-and-facts.html)

Tested for  
Heavy metals  
(Conducted by the German Institute of Environment in Bremen, 2015)



Color: Cranberry 321  
Collection: Rodeo SOFT  
Thickness: 1,4 - 1,6 mm



# DATA SHEET



## Results of the examination for heavy metals

Heavy metals	K 2263 FL I-4 Ecopell 321 Cranberry KW 40 (mg/kg)	BG (mg/kg)	Requirements IVN Leather (mg/kg)	Requirements ECARF (mg/kg)
Antimony	1	0,5	1	–
Aluminium	30	10	500	–
Arsenic	<0,5	0,5	1	–
Lead	<0,5	0,5	1	–
Cadmium	<0,2	0,2	0,2	–
Chrome	21	1	50	40
Cobalt	<1	1	5	–
Mercury	<0,1	0,1	0,2	–
Nickel	1	1	5	–
Titanium	<10	10	500	–
Zirconium	<5	5	500	–

BG = limit of determination | NG = detection limit | mg/KG = milligram per kilogram | nn = not detected