


DATA SHEET



TESTED FOR	RESULT	CONFIRM TO DIN
Lightfastness:	3+	54004
Possible color change:		
Abrasion values:	Level:	
Dry	4 - 5	53339
Wet	4 - 5	
Perspiration	4 - 5	
Permanent folding behavior: 20.000 bucklings	passed	53340
Tensile strength: 20 N/mm	passed	53329
Burning behavior: y EN1021 part I u. II	passed	
Detaillied information about light fastness, abrasion values, skin tollernace and burning behaviour can be found at: www.vegetable-tanned-leather.com/data-and-facts.html		
Tested for Heavy metals, aniline (Conducted by the German Institute of Environment in Bremen, 2013/2015)		

KHAKI 215



Color: Khaki 215
Collection: Nappa
Thickness: 1,4 - 1,6 mm



* Valid only for skins from eco farming
(Please ask for availability)

DATA SHEET



Results of the examination for aniline

Parameter	K 2407 FL-8 Ecopell 215 Khaki KW 49 (mg/kg)	NG (mg/kg)	Requirements IVN Leather (mg/kg)
Aniline	nn	3	≤ 60*

* Sum limit for further amines going beyond European legislation
(2,4 Xylidine, N,N. Dimethylaniline, 5-Chlorine-o-toluidine, p-Phenylenediamine and Aniline)

Results of the examination for heavy metals

Heavy metals	G 9918 FL-4 Ecopell 215 Khaki KW 48 (mg/kg)	BG (mg/kg)
Antimony	<0,2	0,2
Aluminium	70	10
Arsenic	<1	1
Lead	<0,1	1
Cadmium	<0,2	0,2
Chrome	8	1
Cobalt	<1	1
Mercury	<0,2	0,2
Nickel	<1	1
Titanium	<10	10
Zirconium	<15	5

BG = limit of determination | NG = detection limit | mg/KG = milligram per kilogram | nn = not detected